

# Traditional High Satinwood

Technical Data Sheet – F211

# PRODUCT DESCRIPTION & USE

**Fleetwood Traditional Satinwood** is a solvent based midsheen based enamel for interior and exterior surfaces. Formulated to give excellent flow and producing a hard wearing abrasion resistant washable finish. For best results use in conjunction with Fleetwood Undercoat.

### **KEY BENEFITS**

- A high quality gloss finish for interior and exterior use.
- Based on a high quality durable alkyd resin.
- Excellent opacity.

#### **AVAILABLE IN SIZES**



**Fleetwood Traditional Satinwood** White

#### VOC CONTENT

Contains max VOC; 296g/l

Conforms to EU 2010 Directive (Cat A/d) 300g/l

#### **COMPOSITION (NOMINAL)**

Pigment:Lightfast Pigments.Binder:Long oil alkyd resinSolvent:De-aromatized white spirit

## SOLIDS - SPECIFIC GRAVITY

 $\begin{array}{lll} \mbox{Volume Solids} & 55\% \ (+/-2\%) \\ \mbox{Weight Solids} & 70\% \ (+/-2\%) \\ \mbox{Specific Gravity} & 1.35g/l \ (+/-0.02) \\ \end{array}$ 

# **SURFACE PREPARATION**

All surfaces must be clean, dry and free from all defective or poorly adhering material. Thoroughly rub down previously painted surfaces, using 'wet "flatting' methods where possible, wipe off with a damp, lint free cloth. Treat knots with a suitable knotting solution. New or bare surfaces should be primed with an appropriate primer. **Note:** Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain lead (Pb). Use in accordance with good painting practices

# **APPLICATION**



This product may be spray applied but for H&S reasons related to all solvent-based paints, spray application is not recommended. As with other solvent-based paints, do not apply in temperatures below  $5^{\circ}\text{C}$  (as recommended by British Standard BS 6150).

#### SPREADING RATE



As a guide a coverage rate of up to 16m<sup>2</sup> per litre can be achieved under normal conditions

#### TRANSPORTATION & STORAGE

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

#### SPRAY RECOMMENDATIONS

**Conventional Spray:** Satisfactory through most equipment. **Airless Spray:** A typical recommendation for airless spray application is a minimum working pressure on paint of 140 kg/cm<sup>2</sup> (2000 lb/sq in) with a spray tip size of 0.38mm to 0.46mm (15 - 18thou) spray tip angle 65°. Filter mesh 60

#### DRYING TIMES (SINGLE COAT, STANDARD THICKNESS)



**Touch Dry:** 4 - 6 hours **Recoat:** 16 -24 hours **Hard Dry -** 48 hours

This is dependent upon temperature and humidity. Darker colors may take longer.  $26^{\circ}\text{C}$  to 50% RH @ 4 Thou wet

#### **CLEANING UP**



Remove as much product as possible from application equipment before cleaning. Replace lid firmly. Clean equipment immediately after use with White Spirit or Turpentine Substitute. Dispose of cans and waste paint in accordance with local authority guidelines

#### TINTING INSTRUCTIONS

Tint only with Fleetwood tinting systems

#### **PRECAUTIONS**

Keep out of reach of children. Ensure good ventilation during application and drying. Flammable- keep away from sources of ignition. If the product comes in contact with the eyes rinse immediately with plenty of water. To remove splashes from skin use soap and water or a recognised skin cleaner. Do not take internally. **Contains no added lead.** 

# PREVIOUSLY PAINTED SURFACES

If in sound condition, clean the surface of all foreign material. Glossy surfaces must be rubbed down to provide a key. If paint is peeling or badly weathered, clean to sound substrate and treat as new.

# **FOLLOW US ON**

Online: www.fleetwood.ie

Email: info@fleetwood.ie Phone: 049 8547209







