


PRODUCT DESCRIPTION & USE

Fleetwood Trade Soft Sheen is a low sheen emulsion paint that exhibits very good scrub ability. It is burnish, scuff and staining resistance. Fleetwood Trade Soft Sheen is washable and Fleetwood recommends it for all interior surfaces. It is particularly suited to kitchens, bathrooms and other areas that routinely experience moisture.

KEY BENEFITS

- Excellent durability
- Mid sheen finish.
- High opacity

AVAILABLE IN SIZES



COLOUR RANGE

Fleetwood Trade Soft Sheen

Brilliant White and various colours from Colour Answers Tinting Machine.

VOC CONTENT

Contains max VOC; 20g/l
Conforms to EU 2010 Directive (Cat A/a) 30g/l

COMPOSITION (NOMINAL)

Pigment: Lightfast Pigments.
Binder: Acrylic Modified Copolymer Emulsion.
Solvent: Water.

SOLIDS - SPECIFIC GRAVITY

Volume Solids 28% (+/- 1%)
Weight Solids 42.5% (+/- 1%)
Specific Gravity 1.26g/l (+/- 0.1)

SURFACE PREPARATION

Surfaces to be painted must be in sound condition. Use in accordance with good painting practice. Remove oil, grease and flaking material. Treat powdery surfaces with Fleetwood Masonry Primer. Surfaces to be painted must be sound, clean, dry and free from all defective or poorly adhering material, dirt, grease and salts. New plaster and masonry must be fully dry before priming. Treat powdery surfaces with Fleetwood Masonry Primer. Use in accordance with good painting practices

APPLICATION



Temperature (air, surface, material) (at least 4°C above dew point).
10°C to 42°C. Relative Humidity 75% Maximum.

SPREADING RATE



As a guide a coverage rate of up to 12m²/litre can be achieved on non-porous surfaces under normal conditions.

REDUCTION

Reduce by up to 20% as required by application and or equipment.

SPRAY RECOMMENDATIONS

Conventional Spray: Satisfactory through most equipment.

Airless Spray: A typical recommendation for airless spray application is a minimum working pressure on paint of 140 kg/cm² (2000 lb/sq in) with a spray tip size of 0.38mm to 0.46mm (15 - 18thou) spray tip angle 65°. Filter mesh 60

DRYING TIMES (SINGLE COAT, STANDARD THICKNESS)



Touch Dry: 30 Mins

Recoat: 2- 4 hours

This is dependent upon temperature and humidity. Darker colors may take longer.
26°C to 50% RH @ 4 Thou wet.

CLEANING UP



Clean up with soap and water. After cleaning up be sure to flush spray equipment with solvent to prevent rusting following manufacturer's instructions. Dispose of can in accordance with local authority guidelines.

TINTING INSTRUCTIONS

Tint only with Fleetwood tinting systems

PRECAUTIONS

Keep out of reach of children. Ensure good ventilation during application and drying. If the product comes in contact with the eyes rinse immediately with plenty of water. To remove splashes from skin use soap and water or a recognised skin cleaner. Do not take internally. **Contains no added lead.**

PREVIOUSLY PAINTED SURFACES

If in sound condition, clean the surface of all foreign material. Glossy surfaces must be rubbed down to provide a key. If paint is peeling or badly weathered, clean to sound substrate and treat as new.

FOLLOW US ON

Online: www.fleetwood.ie

Email: info@fleetwood.ie

Phone: 049 8547209

