Fleetwood

TECHNICAL F631

## **BROOKS MASONRY PAINT**

CHARACTERISTICS	APPLICATION	SURFACE PREPARATION
A smooth exterior emulsion paint of superior quality, it is formulated to provide excellent exterior durability and resistance to organic growth.	Temperature (air, surface, material) (at least 4°C above dew point) 10°C to 42°C. Relative Humidity 75% Maximum.	Surfaces to be painted must be in sound condition. Use in accordance with good painting practice. Remove oil, grease and flaking material. Treat powdery surfaces with Water Based Stabilising Solution.
	SPREADING RATE	
COLOUR		
Brilliant White and various colours	METHODS Brush, roller, airless spray	Steel:- Remove all loose rust, peeling paint, other loosely adhering contaminations per SSPC SP2. Hand
DRYING SCHEDULE	Airless Spray:- Minimum pressure 138 bars (2000lb/sq in).	tool cleaning. Remove any
(Temperature and humidity dependant) @ 26°C 50% RH @ 4Thou Wet To Touch - 30 mins To Dry - 4 hours	Tip Size:- 0.38mm - 0.46mm (15-18 Thou). Filter:- 60 mesh. Angle:- 65 degrees	
SPECIFIC GRAVITY	Always flush spray equipment with water prior to applying Water Based Coatings.	Concrete Block and Masonry:- Surfaces should be thoroughly clean and dry, with
1.27+\-0.15		mortar and concrete aired for a minimum
	MIXING INSTRUCTIONS	of 30 days @ 24°C. All loose mortar or
WEIGHT SOLIDS 45+\-2%	Thoroughly mix paint before use by stirring and boxing.	other contaminants should be removed prior to application of any coating material. Surface temperatures must be
VOLUME SOLIDS	PERFORMANCE INFORMATION	at least 12°C before filling. Use appropriate filler for cracks or
CL CL CL CL CL CL CL CL CL CL CL CL CL C	The product is specially designed as an exterior coating for use over block, concrete and other masonry surfaces where a long lasting decorative finish is required.	Galvanised:- The surface should be exterior weathered for 6 months prior to painting, solvent clean per SSPC-SP1.
	Clean up with soap and water. After clean up be sure to flush spray equipment with solvent to prevent rusting following manufacturers instructions.	When weathering is not possible, surface must be solvent cleaned followed by an appropriate etch prime. Rusty galvanised surfaces must be hand tool cleaned per SSPC-SP2. Prime rust areas with
		appropriate anti-corrosive primer.
	REDUCTION	PREVIOUSLY PAINTED SURFACES
	Reduce up to 20% with water as required by application equipment	If in sound condition, clean the surface of
PRECAUTIONS		all foreign material. Glossy surfaces
Keep out of reach of children. Ensure good ventilation during application and drying.		must be rubbed down to provide a key. If paint is peeling or badly weathered, clean to sound substrate and treat as new.
In case of contact with eyes rinse immediately with plenty of water.		
To remove splashes from skin use soap and water or a recognised skin cleaner. Do not take internally. Contains no added lead.		
and water or a recognised skin cleaner. Do not take internally.	I to Virginia Co Cavan Iroland Tel	ISSUE NO. +353 49 8547209 Fax +353 49 84

Fleetwood Paints Ltd/FSW Coatings Ltd., Virginia, Co.Cavan. Ireland. Tel +353 49 8547209 Fax +353 49 8547470 Email: info@fleetwood.ie info@fsw.ie Web: www.fleetwood.ie