

MELAMINE & Kitchen Cabinet Primer

CHARACTERISTICS:	APPLICATION:	THINING:	
FLEETWOOD MELAMINE & Kitchen Cabinet Primer is the ideal choice as a primer coat for kitchen units. It is formulated to give excellent adhesion for subsequent coats of paint on these difficult surfaces.	Stir thoroughly before use and apply using a synthetic brush or mohair roller. Apply 2 coats. Do not apply in temperatures below 10°C. Apply with a synthetic (nylon, polyester or blend) bristle brush, roller, pad applicator or airless sprayer	Normal use (not to be exceeded): Add up to 1 part clean water to 10 parts paint. Conventional spray application: Add up to 1 part clean water to 2.5 parts paint. Airless spray application: Add up to 1 part clean water to 5 parts paint.	
RECOMMENDED USE: FLEETWOOD MELAMINE & Kitchen Cabinet Primer is ideal for use in kitchens and bathrooms or other surfaces. Most paints either water or oil based will excellent adherence to this coating.			
AVAILABILITY: 500 ml 1.0 – 2.5 litre	SURFACE PREPARATION To get the best results, ensure surfaces to be painted are sound, clean and dry and free from all defective or poorly adhering material such as dirt, grease or wax. Remove any existing dirt, grease, or other contamination before preparation. Lightly sand surface to be coated and lightly sand 1 st coat of primer before applying topcoat. Fleetwood Advanced Satin or similar products provide an excellent top coat for kitchen cabinet finish.	SPRAY RECCOMENDATIONS: Conventional Spray: Satisfactory through most equipment. Airless Spray: A typical set up for airless spray application would be a minimum working pressure on paint of 133 bars with a spray tip size of 0.43mm and a spray tip angle of 60°C	
FINISH: Matt			
COLOUR: White			
SPECIFIC GRAVITY: 1.23 +/- 0.2			
VOC: 30g/litre			
VOLUME SOLIDS: 36%			
SPREADING RATE: 8m ² per litre			
DRYING TIME: Touch Dry 2 hour Recoat 12 hours			
PRECAUTIONS: Keep out of reach of children. Ensure good ventilation during application and drying. In case of contact with eyes rinse immediately with plenty of water. To remove splashes from skin use soap and water or a recognised skin cleaner. Do not take internally. Contains no added lead.			CLEAN UP: Clean up with soap and water. After clean-up be sure to flush any spray equipment with solvent to prevent rusting.