

Extra Plus Vinyl Matt


PRODUCT DESCRIPTION & USE

Fleetwood Extra Plus Vinyl Matt is especially formulated for the professional painter. This product provides a combination of excellent coverage, whiteness and application. This product also offers high breathability and water vapour permeability.

KEY BENEFITS

- · Excellent durability, high opacity
- Class 'O' Flame retardance on a class 'O' surface in accordance with BS476 part 6: 1989.
- · Flat matt finish
- · High opacity
- · Water vapour permeable

AVAILABLE IN SIZES



COLOURRANGE

Fleetwood Extra Plus Vinyl Matt Base

Available in brilliant white and various colours through the Colour Answers Tinting System

VOC CONTENT

Contains max VOC; 8 g/l Conforms to EU 2010 Directive (Cat A/a) 30g/l



COMPOSITION (NOMINAL)

Pigment: Lightfast Pigments.

Binder: Acrylic Modified Copolymer Emulsion

Solvent: Water.

MATERIAL CHARACTERISTICS

 Volume Solids (P Base)
 34% (+/- 2%)

 Weight Solids
 55% (+/- 2%)

 Specific Gravity
 1.47 g/l (+/- 0.15)

Water vapour transmission

rate $V > 1,100 \text{ g/m}^2/\text{d}$

Gloss at 85° < 6.0 pH -Value > 8.2

SURFACE PREPARATION

Surfaces to be painted must be in sound condition. Use in accordance with good painting practice. Remove oil, grease and flaking material. Treat powdery surfaces with Fleetwood Masonry Primer. Surfaces to be painted must be sound, clean, dry and free from all defective or poorly adhering material, dirt, grease and salts. New plaster and masonry must be fully dry before priming. Treat powdery surfaces with Fleetwood Masonry Primer. Use in accordance with good painting practices

APPLICATION



Temperature (air, surface, material) (at least $4 \, ^{\circ}\text{C}$ above dew point). $10 \, ^{\circ}\text{C}$ to $42 \, ^{\circ}\text{C}$. Relative humidity 75% Maximum.

SPREADING RATE



As a guide a coverage rate of up to 15m²/l can be achieved under normal conditions

REDUCTION

Reduce by up to 20% as required by application and or equipment. When applying over previously painted matt surfaces, it is good practice to apply the 1st coat at 105 dilutions.

SPRAY RECOMMENDATIONS

Conventional Spray: Satisfactory through most equipment. **Airless Spray:** A typical recommendation for airless spray application is a minimum working pressure on paint of 140 kg/cm^2 (2000lbs/sq in) with a spray tip size of 0.38 mm to 0.46 mm (15 - 18 thou) spray tip angle 65° . Filter mesh 60

DRYING TIMES (SINGLE COAT, STANDARD THICKNESS)



Touch Dry: 30 Mins **Recoat:** 4 hours

This is dependent upon temperature and humidity. Darker colors may take longer. $26 \, ^{\circ}\text{C}$ to 50 % RH @ 4 Thou wet.

CLEANING UP



Clean up with soap and water. After cleaning up be sure to flush spray equipment with solvent to prevent rusting following manufacturer's instructions. Dispose of can in accordance with local authority guidelines.

TINTING INSTRUCTIONS

Tint only with Fleetwood tinting systems

PRECAUTIONS

Keep out of reach of children. Ensure good ventilation during application and drying. If the product comes in contact with the eyes rinse immediately with plenty of water. To remove splashes from skin, use soap and water or a recognised skin cleaner. Do not take internally. **Contains no added lead.**

PREVIOUSLY PAINTED SURFACES

If in sound condition, clean the surface of all foreign material. Glossy surfaces must be rubbed down to provide a key. If paint is peeling or badly weathered, clean to sound substrate and treat as new.

FOLLOW US ON

Online: www.fleetwood.ie Email: info@fleetwood.ie Phone: 049 8547209







