


PRODUCT DESCRIPTION & USE

Fleetwood Quick Dry Masonry Stabilising Primer is a high performance quick drying alkali resistant primer and sealer. It provides an excellent key to consolidate and bind friable or porous masonry surfaces prior to decoration. The problems of toxicity, smell and flammability of solvent based resin solutions is eliminated by the use of this water based low VOC product. The product seals plaster, plasterboard, cement render, bare masonry, window sill, pier capping, and fibre cement boards, giving excellent penetration and providing a stable base.

KEY BENEFITS

- A high quality, water-based low odour low VOC.
- Excellent penetration binding powdery surfaces.
- Provides a sound surface for subsequent coats.

AVAILABLE IN SIZES



COLOUR RANGE

Fleetwood Quick Dry Masonry Stabilising Primer

Available in clear solution only.

VOC CONTENT

Contains max VOC; 3g/l
 Conforms to EU 2010 Directive (Cat A/c) 40g/l

COMPOSITION (NOMINAL)

Binder: Acrylic Modified Copolymer Emulsion.
Solvent: Water.

SOLIDS - SPECIFIC GRAVITY

Volume Solids 16.0 % (+/- 2%)
Weight Solids 17.0 % (+/- 2%)
Specific Gravity 1.02 g/l (+/- 0.15)

SURFACE PREPARATION

Surfaces to be coated must be clean, dry, and free from all defective or poorly adhering material, dirt, grease, and salts. New plaster and masonry must be fully dry before priming. Use in accordance with good painting practices. Stir well before use. Apply one full coat, preferably brushing firmly into the surface. Porous surfaces should be sealed with a first coat of Quick Dry Masonry Stabilising Primer. Allow 3 hours to dry under normal conditions before applying the required paint finish. For best results, apply by brush as this assists the primer to penetrate the surface. Alternatively Quick Dry Masonry Stabilising Primer can be applied by airless spray.

APPLICATION



Brush, roller, spray & airless spray.
 As with other water-based paints, do not apply in temperatures below 5°C.

SPREADING RATE



As a guide a coverage rate of between 10 - 12m²/litres can be achieved under normal conditions

SPRAY RECOMMENDATIONS

Conventional Spray: Satisfactory through most equipment.
Airless Spray: A typical recommendation for airless spray application is a minimum working pressure on paint of 140 kg/cm² (2000 lb/in²) with a spray tip size of 0.38mm to 0.46mm (15 - 18thou) spray tip angle 65°. Filter mesh 60

DRYING TIMES (SINGLE COAT, STANDARD THICKNESS)



Touch Dry: 2 hours.
Recoat: 3 - 4 hours

This is dependent upon temperature and humidity. Darker colours may take longer.

CLEANING UP



Clean up with soap and water. After cleaning up be sure to flush spray equipment with solvent to prevent rusting following manufacturer's instructions. Dispose of can in accordance with local authority guidelines.

PRECAUTIONS

Keep out of reach of children. Ensure good ventilation during application and drying. If the product comes in contact with the eyes rinse immediately with plenty of water. To remove splashes from skin, use soap and water or a recognised skin cleaner. Do not take internally. **Contains no added lead.**

PREVIOUSLY PAINTED SURFACES

If in sound condition, clean the surface of all foreign material. If paint is peeling or badly weathered, clean to sound substrate and treat as new.

FOLLOW US ON

Online: www.fleetwood.ie
 Email: info@fleetwood.ie
 Phone: 049 8547209

