



Fleetwood

TECHNICAL DATA

F711

JACOBI SUPER SID

CHARACTERISTICS	APPLICATION	SURFACE PREPARATION
Super Sid Matt Emulsion is an economic white matt designed to provide a smooth matt finish on interior walls and ceilings.	Temperature (air, surface, material) (at least 4°C above dew point) 10°C to 42°C. Relative Humidity 75% Maximum.	Surfaces to be painted must be in sound condition. Use in accordance with good painting practice. Remove wax, rust, grease, oil, flaking material and powdery substances. Lightly sand glossy surfaces. Follow by thoroughly washing with detergent and rinsing with clean water. Check coloured and gold marked wallpaper for colour bleeding through. If this occurs, apply an appropriate sealer. Allow to dry. Areas with uneven porosity may require a coat of Water Based Stabilising Solution.
COLOUR	SPREADING RATE	Concrete Block and Masonry:- Surfaces should be thoroughly clean and dry, with mortar and concrete aired for a minimum of 30 days @ 24°C. All loose mortar or other contaminants should be removed prior to application of any coating material. Surface temperatures must be at least 12°C before filling. Use appropriate filler for cracks or imperfections. Allow to dry thoroughly before top-coating.
White	120m ² /10lt 60m ² /5lt 30m ² /2.5lt	PREVIOUSLY PAINTED SURFACES
DRYING SCHEDULE	METHODS	If in sound condition, clean the surface of all foreign material. Glossy surfaces must be rubbed down to provide a key. If paint is peeling or badly weathered, clean to sound substrate and treat as new.
(Temperature and humidity dependant) @ 26°C 50% RH @ 4 Thou wet. To Touch - 30 mins To Dry - 4 hours	Brush, roller, airless spray. Airless Spray:- Minimum pressure 138 bars (2000lb.sq in). Tip Size:- 0.38mm - 0.46mm (15-18 Thou). Filter:- 60 mesh. Angle:- 65 degrees Always flush spray equipment with water prior to applying Water Based Coatings.	ISSUE NO.1 1/2012
SPECIFIC GRAVITY	MIXING INSTRUCTIONS	
1.63+/-0.05	Thoroughly mix paint before use by stirring and boxing.	
WEIGHT SOLIDS	TINTING INSTRUCTIONS	
60+	Tint only with the Fleetwood Tinting System.	
VEHICLE TYPE	CLEAN UP	
Vinyl Copolymer Emulsion	Clean up with soap and water. After clean up be sure to flush spray equipment with solvent to prevent rusting following manufacturers instructions.	
VISCOSITY (Initial)	REDUCTION	
above 80 KU	Reduce up to 10% with water as required by application equipment.	
PH (Initial)		
above 8.2		
PRECAUTIONS		
<p>Keep out of reach of children. Ensure good ventilation during application and drying.</p> <p>In case of contact with eyes rinse immediately with plenty of water.</p> <p>To remove splashes from skin use soap and water or a recognised skin cleaner. Do not take internally.</p> <p>Contains no added lead.</p>		