



STAINS

Blocking Primer

· ·		
CHARACTERISTICS:	APPLICATION:	THINING:
FLEETWOOD Stains Blocking	Stir thoroughly before use and	Normal use (not to be exceeded):
Primer is a quick drying interior stain preventative primer.	apply using a synthetic brush or	Add up to 1 part clean water to 10
RECOMMENDED USE:	mohair roller. Apply 2 coats. Do	parts paint.
FLEETWOOD Stains Blocking	not apply in temperatures below	Conventional spray application:
Primer is a multi-surface primer	10°C.	Add up to 1 part clean water to 2.5
designed to seal in common stains such as coffee, tea, wine,		parts paint.
permanent marker, grease spots,		Airless spray application:
crayons and ketchup from bleeding through into the top-coat.		Add up to 1 part clean water to 5 parts
and and top dod.		paint.
AVAILABILITY:	SURFACE PREPARATION	VOC:
0.5 – 1.0 – 2.5litre	To get the best results, ensure	16g/litre
FINISH:	surfaces to be painted are sound,	SPRAY RECCOMENDATIONS:
Flat matt	clean and dry (new surfaces	Conventional Spray:
COLOUR:	particularly must be fully dry) and free	Satisfactory through most equipment.
White	from all defective or poorly adhering	
SPECIFIC GRAVITY:	material such as dirt, grease or wax.	Airless Spray:
1.29 +/- 0.2		A typical set up for airless spray
VOLUME SOLIDS:	If there is heavy soiling it is	application would be a minimum
34%	recommended that the surface to be	working pressure on paint of 133 bars
SPREADING RATE:	primed is washed thoroughly with a	with a spray tip size of 0.43mm and a
12m ² per litre	detergent such as sugar soap.	spray tip angle of 60°C
DRYING TIME:	Allow the surface to dry completely	
Touch Dry 30 minutes	before priming. Stain ghosting can	
Recoat 4 hours	sometimes be present in the primer	
PRECAUTIONS:	coat but this <u>will not</u> migrate into the	CLEAN UP:
Keep out of reach of children. Ensure	top-coat	Clean up with soap and water. After
good ventilation during application and		clean-up be sure to flush any spray
drying. In case of contact with eyes rinse		equipment with solvent to prevent
immediately with plenty of water. To		rusting.
remove splashes from skin use soap and water or a recognised skin		
cleaner.		
Do not take internally. Contains no added lead.		