

TECHNICAL DATA

F881

TELFORDS VALUE MATT

CHARACTERISTICS

Telfords Matt Emulsion is an economic white matt designed to provide a smooth flat finish on interior walls and ceilings.

COLOUR

White

DRYING SCHEDULE

(Temperature and humidity dependant) @ 26°C 50% RH @ 4 Thou wet. To Touch - 30 mins To Dry - 4 hours

SPECIFIC GRAVITY

1.36+/-0.01

WEIGHT SOLIDS

43+/-1%

VEHICLE TYPE

Vinyl Copolymer Emulsion

VISCOSITY (Initial)

above 80 KU

PH (Initial)

above 9

BINDER

Vinyl Emulsion

APPLICATION

Temperature (air, surface, material) (at least 4°C above dew point) 10°C to 42°C. Relative Humidity 75% Maximum.

SPREADING RATE

120m²/10lt 60m²/5lt 30m²/2.5lt

METHODS

Brush, roller, airless spray.

Airless Spray:- Minimum pressure 138 bars (2000lb.sq in).

Tip Size:- 0.38mm - 0.46mm (15-18

Thou).

Filter:- 60 mesh. Angle:- 65 degrees

Always flush spray equipment with water prior to applying Water Based Coatings.

MIXING INSTRUCTIONS

Thoroughly mix paint before use by stirring and boxing.

TINTING INSTRUCTIONS

Tint only with the Fleetwood Tinting System.

CLEAN UP

Clean up with soap and water. After clean up be sure to flush spray equipment with solvent to prevent rusting following manufacturers instructions.

REDUCTION

Reduce up to 10% with water as required by application equipment.

SURFACE PREPARATION

Surfaces to be painted must be in sound condition. Use in accordance with good painting practice. Remove wax, rust, grease, oil, flaking material and powdery substances. Lightly sand glossy surfaces. Follow by thoroughly washing with detergent and rinsing with clean water. Check coloured and gold marked wallpaper for colour bleeding through. If this occurs, apply an appropriate sealer. Allow to dry. Areas with uneven porosity may require a coat of Water Based Stabilising Solution.

Concrete Block and Masonry:- Surfaces should be thoroughly clean and dry, with mortar and concrete aired for a minimum of 30 days @ 24°C. All loose mortar or other contaminants should be removed prior to application of any coating material. Surface temperatures must be at least 12°C before filling. Use appropriate filler for cracks or imperfections. Allow to dry thoroughly before top-coating.

PREVIOUSLY PAINTED SURFACES

If in sound condition, clean the surface of all foreign material. Glossy surfaces must be rubbed down to provide a key. If paint is peeling or badly weathered, clean to sound substrate and treat as new.

PRECAUTIONS

Keep out of reach of children. Ensure good ventilation during application and drying.

In case of contact with eyes rinse immediately with plenty of water.

To remove splashes from skin use soap and water or a recognised skin cleaner. Do not take internally.

Contains no added lead.

ISSUE NO.1 9/2009

Fleetwood Paints Ltd/FSW Coatings Ltd., Virginia, Co.Cavan. Ireland. Tel +353 49 8547209 Fax +353 49 8547470

Email: info@fleetwood.ie info@fsw.ie Web: www.fleetwood.ie