



**TECHNICAL
DATA**

F827

TOPLINE CEILING PAINT

<p>CHARACTERISTICS</p>	<p>APPLICATION</p>	<p>SURFACE PREPARATION</p>
<p>A high opacity, high whiteness contract matt emulsion paint. Provides excellent obliteration and breathability on new interior plaster.</p>	<p>Temperature (air, surface, material) (at least 4°C above dew point) 10°C to 42°C. Relative Humidity 75% Maximum.</p>	<p>Surfaces to be painted must be in sound condition. Use in accordance with good painting practice. Remove oil, grease and flaking material. Treat powdery surfaces with Fleetwood Masonry Primer-F401.</p>
<p>DRYING SCHEDULE</p>	<p>SPREADING RATE</p>	
<p>(Temperature and humidity dependant) @ 26°C 50% RH @ 90 microns wet. To Touch:- 30 mins To Dry:- 4 hours</p>	<p>12m²/1 litre 120m²/10 litre</p>	
<p>SPECIFIC GRAVITY</p>	<p>METHODS</p>	
<p>1.4+/-0.01</p>	<p>Brush, roller, airless spray. Airless Spray:- Minimum pressure 138 bars (2000lb.sq in). Tip Size:- 0.38mm - 0.46mm (15-18 Thou). Filter:- 60 mesh. Angle:- 65 degrees Always flush spray equipment with water prior to applying Water Based Coatings.</p>	
<p>WEIGHT SOLIDS</p>	<p>MIXING INSTRUCTIONS</p>	
<p>46+/-1%</p>	<p>Thoroughly mix paint before use by stirring and boxing.</p>	
<p>VOLUME SOLIDS</p>	<p>TINTING INSTRUCTIONS</p>	
<p>28+/-1%</p>	<p>Tint only with the Fleetwood Tinting System.</p>	
<p>PRECAUTIONS</p>	<p>CLEAN UP</p>	
<p>Keep out of reach of children. Ensure good ventilation during application and drying. In case of contact with eyes rinse immediately with plenty of water. To remove splashes from skin use soap and water or a recognised skin cleaner. Do not take internally. Contains no added lead.</p>	<p>Clean up with soap and water. After clean up be sure to flush spray equipment with solvent to prevent rusting following manufacturers instructions</p>	
<p>REDUCTION</p>	<p>Reduce up to 10% with water as required by application equipment.</p>	
		<p style="text-align: right;">ISSUE NO.1 9/2012</p>