


### PRODUCT DESCRIPTION & USE

Fleetwood Weatherguard Pliolite® Extreme is a solvent-based paint formulated for exterior use on cement rendering, rough cast, brick and concrete. It provides a smooth matt finish that has excellent adhesion to previously painted and suitably sealed surfaces. This product incorporates a Pliolite® resin which enables application at temperatures down to -5°C and becomes showerproof in 20 minutes, allowing all year round exterior decoration

### KEY BENEFITS

- Solvent borne highly durable coating
- Shower proof in 20 minutes allowing all year round application
- Excellent adhesion to previously painted or untreated porous surfaces
- High opacity

### AVAILABLE IN SIZES



### COLOUR RANGE

Fleetwood Weatherguard Pliolite® Extreme Available in brilliant white and tintable to pastel colours. Dark colours available on request.

### VOC CONTENT

Contains max VOC; 428g/l  
Conforms to EU 2010 Directive (Cat A/c) 430g/l

### COMPOSITION (NOMINAL)

**Pigment:** Lightfast Pigments.  
**Binder:** Pliolite binder®  
**Solvent:** White spirit

### SOLIDS - SPECIFIC GRAVITY

Volume Solids Base P 35% (+/- 2%)  
Weight Solids 63% (+/- 2%)  
Specific Gravity 1.5 g/l (+/- 0.1)

### SURFACE PREPARATION

All surfaces to be painted should be clean, dry and free from loose and flaking material. Repair cracks and defective areas and treat fungal or algal growth with Fleetwood's Fungicidal Wash as directed.

### APPLICATION



This product may be applied by brush, roller or spray. However for H&S reasons related to all solvent-based paints, spray application is not recommended.

### SPREADING RATE



As a guide a coverage rate of up to 6.5m<sup>2</sup> per litre can be achieved under normal conditions

### TRANSPORTATION & STORAGE

To prevent spillage, please store and transport upright.

### REDUCTION

Reduce by up to 15% with white spirit as required by application and or equipment.

### SPRAY RECOMMENDATIONS

**Conventional Spray:** Satisfactory through most equipment.  
**Airless Spray:** A typical recommendation for airless spray application is a minimum working pressure on paint of 153 kg/cm<sup>2</sup> (2180lb/sq in) with a spray tip size of 0.48mm spray tip angle 65°. Filter mesh 60

### DRYING TIMES (SINGLE COAT, STANDARD THICKNESS)



**Touch Dry:** 20- 30 minutes  
**Recoat:** 16 -24 hours  
**Hard Dry -** 48 hours

This is dependent upon temperature and humidity. Darker colors may take longer.  
26°C to 50% RH @ 4 Thou wet.

### CLEANING UP



Remove as much product as possible from application equipment before cleaning. Replace lid firmly. Clean equipment immediately after use with White Spirit or Turpentine Substitute. Dispose of cans and waste paint in accordance with local authority guidelines

### TINTING INSTRUCTIONS

Tint only pastel colours up 1.5% colourant with Fleetwood tinting systems

### PRECAUTIONS

Keep out of reach of children. Ensure good ventilation during application and drying. Flammable- keep away from sources of ignition. If the product comes in contact with the eyes rinse immediately with plenty of water. To remove splashes from skin use soap and water or a recognised skin cleaner. Do not take internally. **Contains no added lead.**

### PREVIOUSLY PAINTED SURFACES

If in sound condition, clean the surface of all foreign material. If paint is peeling or badly weathered, clean to sound substrate and treat as new.

### FOLLOW US ON

Online: [www.fleetwood.ie](http://www.fleetwood.ie)





Email: [info@fleetwood.ie](mailto:info@fleetwood.ie)

Phone: 049 8547209

# **Weatherguard Extreme**

Issue No2 16/01/2017

## **Technical Data Sheet – F109**