

Trade Vinyl Matt

Formulated for the professional painter and is known throughout the industry for its trusted formula and whiteness



PRODUCT DESCRIPTION

Fleetwood Trade Vinyl Matt goes on fast and dries to a smooth and reliable finish, time after time. It is formulated using the latest technology and materials, and manufactured to internationally accepted quality standards to provide emulsion products with outstanding performance. Trade Vinyl Matt finish has a non reflective appearance that helps hide imperfections and smooths lumps and bumps. This product is ideal for interior walls & ceilings and will extend the maintenance of any decorating project.

USES

- All interior walls & ceilings
- Excellent as first coat on new builds
- Breathable and permeable makes it ideal for period and historic buildings
- Decorators favourite for ceilings

CHARACTERISTICS / ADVANTAGES

- Excellent durability
- LRV Rating 90
- Class 'O' Flame non-combustability on a class 'O' surface in accordance with BS476 part 6: 1989
- Quick drying
- Low VOC and odour
- Easy application by spray
- Excellent coverage and opacity
- Flat matt finish
- Water vapour permeable

APPROVALS / STANDARDS

VOC Content

- 2004/42/EC EU limit value for this product (cat.A/a WB): 30g/l (2010) This product contains max. 2g/l VOC.

EPD

- Independent verification of the declaration and data according to EN ISO 14025:2010

Quality Control


- Manufactured under the auspices of ISO 9001:2015 quality & ISO 14001:2015 environmental management systems.

Non-combustability

- Class 'O' Flame non-combustability on a class 'O' surface in accordance with BS476 part 6: 1989

Water Vapour Permeability

- Water Vapour Permeability (BS EN ISO 7783), Vapour Permeability Classification (EN 1062-1),
- Class: SD V1 High <0.14



Need help? Speak to the experts

Our dedicated team are here to help. If you have any queries on this product, or any product in the Fleetwood range, queries about preparation or application, or can't find your required colour, call us today

Technical Assistance: Email: technical@fleetwood.ie Tel: +353 49 854 7209 (weekdays 9am-5pm)
Colour Advice: Tel: +353 49 854 7209 (weekdays 9am-5pm Saturdays 8am - 4.30pm)



Colour

Colours

Brilliant White & Tinted To Pastal Colours

Colour Collections

Fleetwood Colour Perfect, NCS, Sherwin Williams, Pantone, BS British Standard, & RAL



Specification

Composition	Water-based acrylic.
Number of Components	1
Recommended number of coats	2 coats are recommended. Coverage may vary depending on the profile, porosity of the substrate and application method.
Usage Interior/Exterior	Interior/Exterior (in limited areas)
Application Tools	Brush, roller or spray.
Coverage	Approx. 15m ² per litre, per coat.
Overcoat Times	Recoat after 4 hours.
Curing Time	Touch dry in 30 minutes, fully cured after 7 to 10 days.
Suitable For	New or previously painted drywall, plaster, cement, concrete and other paintable surfaces.
Min. application temperature	4°C
Pack Size	5L, 10L + 17.5L
Shelf Life	3 years in unopened container.
Storage	Do not allow to freeze.
Cleaning Tools	Wash application tools in warm, soapy water immediately after use. .
Principle Limitations	Not intended for application to floors or any surface subject to water immersion or prolonged contact with water including shower enclosures, saunas, steam rooms. Not recommended for use in HVAC duct work.
Please contact us regarding applications not described here	

Product Information

Colour Range:	Brilliant White - tintable to pastel colours using the Fleetwood Colour Answers tinting system.
LRV Range:	90
VOC Content:	Contains max VOC; 2g/l Conforms to EU 2010 Directive (Cat A/a) 30g/l

Composition:	Pigment:	Lightfast Pigments
	Binder:	Acrylic Modified Copolymer Emulsion.
	Solvent:	Water

Solids:	Volume Solids (P Base) 34% (+/- 2%) Weight Solids 55% (+/- 2%) Specific Gravity 1.47 g/l (+/- 0.15) Water vapour transmission rate V > 1,100 g/m2/d Gloss at 85° < 6.0 pH -Value > 8.2
Technical Data Sheet	
Trade Vinyl Matt - T11	

Product Information Cont.

Surface Preparation:	Surfaces to be painted must be in sound condition. Use in accordance with good painting practice. Remove oil, grease and flaking material. Treat powdery surfaces with Fleetwood Masonry Primer. Surfaces to be painted must be sound, clean, dry and free from all defective or poorly adhering material, dirt, grease and salts. New plaster and masonry must be fully dry before priming. Avoid the inhalation of dust. Wear a suitable face mask if dry sanding. Special precautions should be taken during surface preparation or pre-1960s paint surfaces over wood and metal as they may contain harmful lead.		
Application:	Brush, roller, spray & airless spray. As with other water-based paints, do not apply in temperatures below 5°C		
Spreading Rate:	As a guide, a coverage rate of up to 15m² /litre can be achieved under normal conditions		
Reduction:	Reduce by up to 20% as required by application and or equipment. When applying over previously painted matt surfaces, it is good practice to apply the 1st coat at 10% dilutions.		
Spray Recommendations:	Conventional Spray: Satisfactory through most equipment. Airless Spray: A typical recommendation for airless spray application is a minimum working pressure on paint of 140 kg/cm2 (2000 lb/in2) with a spray tip size of 0.38mm to 0.46mm (15 - 18thou) spray tip angle 65°. Filter mesh 60		
Drying Time:	Touch Dry:	30 minutes	
	Recoat:	2 – 4 hours	
	This is dependent upon temperature and humidity. Darker colours may take longer 26°C to 50% RH @ 100 µm		
Cleaning Up:	Clean up with soap and water. After cleaning up be sure to flush spray equipment with solvent to prevent rusting following manufacturer's instructions. Dispose of can in accordance with local authority guidelines.		
Tint Instructions:	Tint only with Fleetwood Tinting systems		
Previsously Painted Surfaces:	Keep out of reach of children. Ensure good ventilation during application and drying. If the product comes in contact with the eyes rinse immediately with plenty of water. To remove splashes from skin, use soap and water or a recognised skin cleaner. Do not take internally. Contains no added lead.		
Precautions:	If in sound condition, clean the surface of all foreign material Glossy surfaces must be rubbed down to provide a key. If paint is peeling or badly weathered, clean to sound substrate and treat as new.		

Limitations:

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practicaexperience, and it is given to the best of our knowledge. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We do not hold gurantee for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice. If you have any queries or concerns about using this product, please contact us before application on +353 49 854 7209 technical@fleetwood.ie

Technical Data Sheet

Trade Vinyl
T11

March 2025
Issue 3