

Traditional Floor Paint

Hard-wearing, slip-resistant finish for concrete and wooden floors.



PRODUCT DESCRIPTION

Traditional Floor Paint is a professional-grade polyurethane-based coating that delivers excellent durability and slip resistance. Resistant to mild chemicals, water, oil, and grease, it transforms and dustproofs floors while providing a safe, easy-to-clean finish. Suitable for light to medium traffic areas, it offers long-lasting performance indoors and out.

USES

- Domestic garages
- Workshop floors
- Walkways and aisles
- Storage and utility rooms
- Exterior walkways and markings

CHARACTERISTICS / ADVANTAGES

- Professional quality, single pack polyurethane coating
- Transforms and dustproofs drab, stained concrete
- Easy to use and keep clean
- Excellent hardness
- Built-in slip resistance
- Resistant to mild chemical attack, water, oil and grease
- Withstands light to medium traffic levels

APPROVALS / STANDARDS

VOC Content

- 2004/42/EC EU limit value for this product (cat.A/i SB): 500g/l (2010) This product contains max. 350g/l VOC.

Quality Control

- Manufactured under the auspices of ISO 9001:2015 quality & ISO 14001:2015 environmental management systems.



NBS



NBS Chorus




Need help? Speak to the experts

Our dedicated team are here to help. If you have any queries on this product, or any product in the Fleetwood range, queries about preparation or application, or can't find your required colour, call us today

Technical Assistance: Email: technical@fleetwood.ie Tel: +353 49 854 7209 (weekdays 9am-5pm)

Colour Advice: Tel: +353 49 854 7209 (weekdays 9am-5pm Saturdays 8am - 4.30pm)



Colour

Colours White, Red, Grey, Yellow, Green & Clear base (for tinting).

Colour Collections Fleetwood Colour Perfect, NCS, Sherwin Williams, Pantone, BS British Standard, & RAL



Specification

Composition	Solvent-based polyurethane
Number of Components	1
Recommended number of coats	2 coats are recommended. 2nd coat can be applied as soon as the 1st coat is dry, and should be applied within 5 days. If more than 5 days elapse, the 1st coat should be lightly abraded before 2nd coat is applied.
Usage Interior/Exterior	Interior/Exterior.
Application Tools	Brush, roller.
Coverage	As a guide, a coverage rate of up to 12m ² per litre can be achieved under normal conditions.
Overcoat Times	
Curing Time	
Suitable For	Areas experiencing light to medium levels of traffic and/or low levels of vehicle traffic. Suitable for exterior use to highlight walkways etc. Not suitable for use on large external areas.
Min. application temperature	5°C
Pack Size	5 L
Shelf Life	3 years in unopened container.
Storage	Do not allow to freeze.
Cleaning Tools	Remove as much product as possible from application equipment immediately after use.
Principle Limitations	Not intended for application to floors or any surface subject to water immersion or prolonged contact with water including shower enclosures, saunas, steam rooms. Not recommended for use in HVAC duct work.
Please contact us regarding applications not described here	

Product Information

Pack Sizes:	5 L
Colour Range:	White, Red, Grey, Yellow, Green & Clear base (for tinting).
LRV Range:	90 (White).
VOC Content:	Contains max VOC: 350g/l Conforms to EU 2010 Directive (Cat A/i) 500g/l
Composition:	Pigment: Lightfast Pigments Binder: Solvent based polyurethane Solvent: De-aromatized white spirit
Solids:	Volume Solids: 56.0% (+/- 2%) Weight Solids: 73.0% (+/- 2%) Specific Gravity: 1.28 (+/- 0.15)

Product Information Cont.

Surface Preparation:

Bare Concrete: Remove surface dust and any light dirt or grease deposits using an etch & clean and solution. Using an etch & clean will provide a good key on smooth bare concrete surfaces. Afterwards, flush with clean water and allow the surface to dry. For the removal of heavier deposits of oil and grease, it is recommended to use an industrial cleaning fluid. Again, flush with clean water and allow the surface to dry.

New Concrete: As a guide, new concrete should be left for four weeks to dry in the summer and six in the winter. The surface should then be prepared using an etch primer and thoroughly rinsed away and left to dry prior to applying this coating.

Pre-Painted Surfaces: Abrade and remove any weak or loose paint. Check remaining paint is well bonded. Very smooth, glossy paint should be lightly abraded to provide a key.

Spreading Rate:

As a guide, a coverage rate of up to 12m² per litre can be achieved under normal conditions.

Transportation & Storage:

Do not use or store in extremes of temperature. Protect from frost.
To prevent spillage, please store and transport upright.

Application:

The paint should be thoroughly stirred and must not be thinned. Apply by roller and work well into the surface. Use a paint brush for edges. Avoid applying the paint too thickly. The second coat can be applied as soon as the first coat is dry (generally 16 hours), and should be applied within 5 days. If more than 5 days elapse, the first coat should be lightly abraded before the second coat is applied. Avoid washing the surface for 7 days.

Drying Time:

DRYING TIME	TOUCH DRY	RECOAT TIME	LIGHT TRAFFIC	FULL USE
10°C	16 hours	24 hours	48 hours	72 hours
20°C	10 hours	16 hours	24 hours	36 hours
30°C	6 hours	16 hours	24 hours	36 hours

Cleaning Up:

Remove as much product as possible from application equipment before cleaning. Replace lid firmly. Clean equipment immediately after use with white spirit or turpentine substitute. Dispose of cans and waste paint in accordance with local authority guidelines.

Tinting Instructions:

Tint only with Fleetwood Tinting systems

Precautions:

Keep out of reach of children. Ensure good ventilation during application and drying. Flammable - keep away from sources of ignition. If the product comes in contact with the eyes, rinse immediately with plenty of water. To remove splashes from skin, use soap and water, or a recognised skin cleanser. Do not take internally. **Contains no added lead.**

Precautions:

This coating is not recommended for areas where cars may stand for long periods of time. As is common with single pack paints of this type, a reaction can take place between the car tyres and the paint, leading to delamination.

Limitations:

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We do not hold guarantee for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice. If you have any queries or concerns about using this product, please contact us before application at +353 49 854 7209 or technical@fleetwood.ie