

PRODUCT DESCRIPTION & USE

Fleetwood Contract Plus is a high-quality matt finish paint, with excellent coverage and great application. It is a high opacity emulsion based on a unique Fleetwood formulation. It is ideal for use on plaster as well as wallboards, concrete, cement rendering, brickwork, and blockwork, suitable for all normal interior wall and ceiling surfaces. Contract Plus is available in multiple pastel colours via the Fleetwood Colour Answers tinting system.

KEY BENEFITS

- Excellent coverage
- Superflat matt finish.
- High opacity

AVAILABLE IN SIZES



COLOUR RANGE

Fleetwood Contract Matt

Available in Brilliant White (can be tinted on Fleetwood tinting system)

VOC CONTENT

Contains max VOC; 6g/l
Conforms to EU 2010 Directive (Cat A/a) 30g/l

COMPOSITION (NOMINAL)

Pigment: Lightfast Pigments.
Binder: Va Veova acrylate copolymer dispersion
Solvent: Water.

SOLIDS - SPECIFIC GRAVITY

Volume Solids 28.10 % (+/- 2%)
Weight Solids 45.7 % (+/- 2%)
Specific Gravity 1.33% (+/-0.15)

SURFACE PREPARATION

Surfaces to be painted must be sound, clean, dry and free from all defective or poorly adhering material. Remove oil, grease and flaking material, feather edges of sound paint. Treat powdery surfaces with Fleetwood Masonry Primer. New plaster and masonry must be fully dry before priming. Fill and fix any holes, cracks, and shallow surface defects with a suitable filler, such as Fleetwood Ready Made Filler. Any glossy or eggshell surfaces should be wet abraded to provide a key. Rinse with clean water to remove all residues and allow to dry.

APPLICATION



Temperature (air, surface, material) (at least 4°C above dew point) 10°C to 42°C. Relative Humidity 75% maximum.

SPREADING RATE



As a guide, a coverage rate of between 12m² and 14m² per litre can be achieved on non-porous surfaces under normal conditions.

REDUCTION

Reduce by up to 20% with clean water as required by application, and or equipment. When applying over previously painted matt surfaces it is good practice to apply the 1st coat at a 10% dilution.

SPRAY RECOMMENDATIONS

Conventional Spray: Satisfactory through most equipment.
Airless Spray: A typical recommendation for airless spray application is a minimum working pressure on paint of 140 kg/cm² (2000 lbs/in²) with a spray tip size of 0.38mm to 0.46mm (15 - 18thou) spray tip angle 65°. Filter mesh 60

DRYING TIMES (SINGLE COAT, STANDARD THICKNESS)



Touch Dry: 1- 2 hours
Recoat: 4 hours

This is dependent upon temperature and humidity. Darker colours may take longer. 26°C to 50% RH @ 4 Thou wet.

CLEANING UP



Clean up with soap and water. After cleaning up be sure to flush spray equipment with solvent to prevent rusting following manufacturer's instructions. Dispose of can in accordance with local authority guidelines.

TINTING INSTRUCTIONS

Tint only with Fleetwood tinting systems

PRECAUTIONS

Keep out of reach of children. Ensure good ventilation during application and drying. If the product comes in contact with the eyes rinse immediately with plenty of water. To remove splashes from skin, use soap and water or a recognised skin cleaner. Do not take internally. **Contains no added lead.**

PREVIOUSLY PAINTED SURFACES

If in sound condition, clean the surface of all foreign material. Glossy surfaces must be rubbed down to provide a key. If paint is peeling or badly weathered, clean to sound substrate and treat as new.

FOLLOW US ON

Online: www.fleetwood.ie
Email: info@fleetwood.ie
Phone: 049 8547209

